


# PAC-CLAD ENERGY STAR® RATED COLORS



## PAC-CLAD Metallic Colors



● Denotes PAC-CLAD Metallic Colors

PAC-CLAD STANDARD COLORS	REFLECTIVITY	EMISSIVITY	3 YEAR EXPOSURE	SRI*	STEEL		ALUMINUM			
					24GA.	22GA.	.032	.040	.050	.063
Almond	0.56	0.83	0.57	64	✓	✓	✓	✓	✓	
Arcadia Green	0.33	0.84	0.32	33	✓		✓			
Berkshire Blue*	0.25	0.84	0.22	23	✓					
Bone White	0.71	0.85	0.71	86	✓	✓	✓	✓	✓	✓
Cardinal Red	0.42	0.84	0.41	45	✓		✓			✓
Charcoal	0.28	0.84	0.28	27	✓		✓			✓
Cityscape	0.37	0.85	0.34	39	✓		✓	✓	✓	
Colonial Red	0.34	0.85	0.33	35	✓		✓	✓	✓	
Dark Bronze	0.27	0.85	0.26	26	✓	✓	✓	✓	✓	✓
Evergreen	0.27	0.85	0.25	26	✓		✓			
Hemlock Green	0.30	0.85	0.31	30	✓	✓	✓			✓
Granite*	0.36	0.84	0.35	37	✓	✓	✓	✓	✓	
Mansard Brown	0.26	0.84	0.24	24	✓	✓	✓	✓	✓	
Medium Bronze	0.30	0.85	0.29	30	✓	✓	✓	✓	✓	✓
Military Blue	0.29	0.84	0.28	28	✓		✓			
Musket Gray	0.32	0.84	0.31	32	✓	✓	✓			✓
Patina Green	0.34	0.85	0.33	35	✓		✓			
Sandstone	0.51	0.83	0.51	57	✓	✓	✓	✓	✓	✓
Sierra Tan	0.38	0.85	0.35	40	✓	✓	✓	✓	✓	
Slate Blue	0.25	0.84	0.27	23	✓		✓			
Slate Gray	0.38	0.84	0.37	40	✓	✓	✓	✓	✓	
Stone White	0.61	0.86	0.59	72	✓	✓	✓	✓	✓	✓
Terra Cotta	0.37	0.84	0.37	39	✓		✓			✓
<b>PAC-CLAD METALLIC COLORS</b>										
Aged Copper	0.27	0.83	0.25	25	✓		✓			✓
Champagne	0.45	0.78	0.41	57	✓		✓			✓
Copper Penny	0.45	0.82	0.42	49	✓		✓	✓	✓	
Silver	0.53	0.80	0.51	59	✓		✓	✓	✓	
Weathered Zinc	0.27	0.80	0.27	23	✓		✓			✓
Zinc	0.30	0.85	0.30	30	✓		✓			✓

### \*LOW GLOSS/LOW SHEEN

**Energy Star® Performance Criteria:** Emissivity uses ASTM C1371/E408. Reflectivity uses ASTM E903/C1549.

PAC-CLAD® Metallic finishes are available from stock at a moderate extra cost. PAC-CLAD® Copper Penny is a Non-Weathering finish.

Solar Reflectance Index calculated according to ASTM E-1980.